

### Glossy Transparent Glazes

Material	Product Code	Description	Temperature °C	Substrate	TEC 20 - 420°C [10 <sup>-7</sup> ] <sup>[1]</sup>
Mixture	12079SP	Transparent, Glossy	960 - 1020	Pottery	70
Mixture	TR2528C	Transparent, Glossy	1000 - 1080	Pottery, Cookware	62
Mixture	TR2469C/RJ	Transparent, Glossy	1000 - 1080	Pottery, Cookware	70
Mixture	TR3441C	Transparent, Glossy	1040 - 1120	Pottery, Cookware	62

### Matt Transparent Glazes

Material	Product Code	Description	Temperature °C	Substrate	TEC 20 - 420°C [10 <sup>-7</sup> ] <sup>[1]</sup>
Mixture	MA2413C/RJ	Matt-satin Transparent	1000 - 1080	Pottery, Cookware	60
Mixture	MA3196C	Dry-mix Transparent, Matt	1150 - 1180	Stoneware, Bricks	55
Mixture	MA4855C	Matt-satin Transparent	1200 - 1250	Stoneware	60

[1] - All TEC values are approximate.

### Glossy White Glazes

Material	Product Code	Description	Temperature °C	Substrate	TEC 20 - 420°C [10 <sup>-7</sup> ] <sup>[1]</sup>
Mixture	OP1553T	Glossy White, Zr-based	960 - 1040	Pottery	60
Mixture	89910	Glossy White, Zr-based	1000 - 1140	Pottery, Cookware	60
Mixture	89884	Glossy White, Sn-based	960 - 1020	Pottery, Tiles	62
Mixture	3088	Glossy White, Sn-based	1000 - 1040	Pottery, Tiles	62

### Matt White Glazes

Material	Product Code	Description	Temperature °C	Substrate	TEC 20 - 420°C [10 <sup>-7</sup> ] <sup>[1]</sup>
Mixture	MA2311T	Matt White	980 - 1020	Pottery	60
Mixture	MA2453T	Matt White	1020 - 1080	Pottery	55

[1] - All TEC values are approximate.

### Effect Glazes

Material	Product Code	Description	Temperature °C	Substrate
Mixture	RU2978R	Effect Brown	980 - 1040	Pottery
Mixture	RU2902T	Effect Base	1040 - 1080	Pottery
Mixture	RU2948C	Effect Base Crème	1040 - 1080	Pottery
Mixture	RU4870E	Gold/bronze Metallic	1200 - 1230	Stoneware
Mixture	TR4646K	Sea-green	1200 - 1230	Stoneware

## Sinter Engobes

Material	Product Code	Description	Temperature °C	Substrate
Mixture	12118SP	White	960 - 1060	Pottery
Mixture	SE1522T	White	1000 - 1080	Pottery, Tiles
Mixture	78126	White	1000 - 1140	Pottery, Tiles