

#### **Technical data**

# Silver brazing filler metal

# Silver-flo™ 30 – Cadmium free silver brazing filler metal

### **Product description**

Silver-flo™ 30 is a cadmium free silver brazing filler metal that has been adopted for a thermal spray coating process used in the aerospace industry. It is supplied as a wire on plastic reels suitable for feeding into a thermal spray gun.

The filler metal itself has a long and high melting range and poor flow characteristics hence it is not used as a brazing filler metal to any extent. Optimum joint gaps at brazing temperature are 0.075-0.2mm.

Composition: 30%Ag, 38%Cu, 32%Zn

Conforms to: EN1044 1999 AG204, ISO 17672:2010 Ag 230, MSRR 9507/113

Melting range: 695-770°C

## **Uses for this product**

This material is used in a thermal spray process in the aerospace industry.

#### **Conditions for use**

Companies should refer to the relevant specification and procedures of the aerospace contractor for conditions for use.

### **Product availability**

Rod	1.5mm dia
Flux coated rod	On request
Wire	3mm
Strip	On request
Foil	On request
Braze-pastes	On request
Others	Rings, Preformed shapes

Johnson Matthey Plc cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products will be used. This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is given in good faith, being based on the latest information available to Johnson Matthey Plc and is, to the best of Johnson Matthey Plc's knowledge and belief, accurate and reliable at the time of preparation. However, no representation, warranty or guarantee is made as to the accuracy or completeness of the information and Johnson Matthey Plc assumes no responsibility therefore and disclaims any liability for any loss, damage or injury howsoever arising (including in respect of any claim brought by any third party) incurred using this information.

The product is supplied on the condition that the user accepts responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. Freedom from patent or any other proprietary rights of any third party must not be assumed. The text and images on this document are Copyright and property of Johnson Matthey. This datasheet may only be reproduced as information, for use with or for resale of Johnson Matthey products. The JM logo©, Johnson Matthey name© and product names referred to in this document are trademarks of Johnson Matthey. Easy-flo® and Silver-flo® are registered to JM in the EU. Sil-fos™ is registered to JM in the UK and certain other countries but is marketed as Mattiphos™ in Germany and the USA.

