

Technical data

Brazing Flux

Silver-flo™ Flux paste

Product description

Silver-flo™ Flux Paste is a brazing flux suitable for use with silver brazing filler metals. It has a working range of 575-775°C and can be used with silver brazing filler metals melting below 725°C (such as several of the Silverflo™, Easy-flo™ and Argo-braze™ alloys).

It is suitable for use on all the common engineering materials, (copper, brass, mild steel and stainless steel), but not aluminium. JM special purpose fluxes are required when brazing aluminium bronze, certain grades of stainless steel, tungsten, molybdenum and tungsten carbide or where protracted heating is involved.

This product is also referred to as Easy-flo™ Low Temperature Grade Paste.

Conforms to: EN 1045: FH10

Working range: 550-775°C

Directions for use

In order to ensure a consistent mixture throughout stir the flux paste well before use. Flux paste should be brushed onto the joint surfaces before assembly. Further flux should then be applied externally either side of the joint mouth.

It is good practice to mechanically clean and degrease the joint surface before applying flux. Heat slowly and evenly to the brazing temperature, without local overheating. Use the flux as a temperature guide - it will become clear or opaque as brazing temperature is approached. If blackening of the flux occurs this is often a sign of insufficient flux, overheating or flux exhaustion.

Flux residue removal

The flux residues of this product, left after completion of the brazing operation, are corrosive and should be removed. They can be readily removed by soaking in hot water at a temperature >40°C for between 15 and 30 minutes. Any remaining residues can then be brushed off in running water.

Product availability

Special order only

Silver-flo™, Easy-flo™ and Argo-braze™ are Johnson Matthey trademarks and are registered to JM in the EU and certain other countries. Johnson Matthey Plc cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products will be used. This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is given in good faith, being based on the latest information available to Johnson Matthey Plc and is, to the best of Johnson Matthey Plc's knowledge and belief, accurate and reliable at the time of preparation. However, no representation, warranty or guarantee is made as to the accuracy or completeness of the information and Johnson Matthey Plc assumes no responsibility therefore and disclaims any liability for any loss, damage or injury howsoever arising (including in respect of any claim brought by any third party) incurred using this information.

The product is supplied on the condition that the user accepts responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. Freedom from patent or any other proprietary rights of any third party must not be assumed. The text and images on this document are Copyright and property of Johnson Matthey. This datasheet may only be reproduced as information, for use with or for resale of Johnson Matthey products. The JM logo®, Johnson Matthey name® and product names referred to in this document are trademarks of Johnson Matthey. Easy-flo® and Silver-flo® are registered to JM in the EU. Sil-fos™ is registered to JM in the UK and certain other countries but is marketed as Mattiphos™ in Germany and the USA.

Johnson Matthey PLC, Platinum Group Metal Services, Orchard Road, Royston, Herts, SG8 5HE, UK Rev.27/01/25.

