



---

# ARGO-BRAZE™

FOR BRAZING OF STAINLESS STEEL JOINTS  
FOR WET ENVIRONMENTS

# ARGO-BRAZE™

## for brazing of stainless steel joints for wet environments

### products at a glance

#### Compositions

The Argo-braze™ products in this brochure have the following compositions:

Alloy System	Additional elements
Ag Cu Ni	In Sn

Argo-braze™ 632 is supplied to ISO17672 Ag463.

Argo-braze™ 56 is a proprietary Johnson Matthey product.

#### Uses for the Products

These specialised Argo-braze™ products are used specifically where there is a need to braze stainless steel and the resulting joints will be subject to aqueous environments in service. This includes both the internal and external part of the joint on a combination of stainless steel and the following materials

- ▶ Steel (carbon/low alloy, tool and stainless)
- ▶ Tungsten carbide and tungsten carbide backed poly-crystalline diamond
- ▶ Copper and copper alloys including brass, bronze, nickel silver and aluminium-bronze

#### Conditions for Use

The Argo-braze™ products are intended for use by brazing in air using a hand torch, fixed burner system, high frequency induction or resistance heating methods.

They should be used with a compatible brazing flux. This can be introduced to the joint by applying a separate flux powder or paste, or a brazing paste with a built in flux binder system.

### specialised corrosion resistant filler metals

These products are used to offer maximum protection against interfacial corrosion in a silver brazed joint on stainless steel exposed to aqueous environments.

Specification	Description	Product Forms	
<b>Argo-braze™ 56</b>	Argo-braze™ 56 was formulated to overcome potential problems of interfacial corrosion on stainless steel components exposed to wet conditions in service. It contains nickel, which has been found to promote resistance to this type of corrosion whilst excluding zinc, which may promote it. Argo-braze™ 56 contains indium, which reduces the melting temperature making it somewhat easier to use than Argo-braze™ 632. It has a long melting range and poor flow characteristics giving rise to large fillets around the joints.		
Ag Cu Ni In Sn			
56 27.25 2.25 14.5 -			
Melting Range °C			600-711
AMS/AWS A5.8			-
EN1044: 1999	AG403	Cd Free	
ISO 17672:2010	Next revision		
<b>Argo-braze™ 632</b>	Argo-braze™ 632 was formulated to overcome potential problems of interfacial corrosion on stainless steel components exposed to wet conditions in service. It contains nickel, which has been found to promote resistance to this type of corrosion whilst excluding zinc, which may promote it. It has a long melting range and poor flow characteristics giving rise to large fillets around the joints. The relatively high brazing temperature and poor flow make it more difficult to use than conventional silver brazing filler metals.		
Ag Cu Ni In Sn			
63 28.5 2.5 - 6			
Melting Range °C		691-802	
AMS/AWS A5.8		4774, BAg-21	
EN1044: 1999	-	Cd Free	
ISO 17672:2010	Ag 463		

### technical considerations for using argo-braze™ 632 & argo-braze™ 56

#### Brazing Technique

Before application of these filler metals the joint area should be at brazing temperature to avoid problems with liquation in which the low melting constituent of the alloy flows first before the alloy is fully molten. A rapid heating method such as induction or an oxy-acetylene torch helps to avoid the problem. Argo-braze™ 632 and Argo-braze™ 56 both have long melting ranges and poor flow characteristics giving rise to large fillets around the joints. Pre-placement of the filler metal requires the heating method to be rapid to prevent liquation.

#### Recommended Flux

On small components Easy-flo™ Stainless Steel Grade Flux or Easy-flo™ 100 Flux Paste are recommended. Where prolonged heating is required Tenacity™ No.5 Flux Powder should be used. See Johnson Matthey Brazing Fluxes brochure for details of these products.

**Caution:** - Boron containing fluxes such as Tenacity™ No.5A Flux Powder, Tenacity™ No.6 Flux Powder or Paste and Tenacity™ No.3A should be avoided as boron is known to promote the onset of interfacial corrosion in silver brazed joints.



# ARGO-BRAZE™

## technical

### interfacial corrosion

Interfacial corrosion is a particular type of failure where silver brazed joints in stainless steel are exposed to water, aqueous solutions or humidity in service. Care must be exercised when selecting alloys for brazing stainless steel where the completed joints will be exposed to these conditions.

Joint failure can be rapid and take only a few months and occurs at the brazing filler metal/stainless steel interface. This phenomenon is commonly referred to as crevice corrosion, but more correctly should be called interfacial corrosion.

#### Conditions That Produce Interfacial Corrosion - Service Environment

To produce a joint failure by interfacial corrosion at least one member of the joint must be made from a stainless steel, the brazing filler metal must be susceptible to this form of attack and the joint must be exposed to damp or wet environments in service.

Research into interfacial corrosion has been conducted using tap water, aqueous solutions of acids and aqueous solutions containing sodium

chloride. All of these solutions produced failure on those joints brazed with susceptible alloys. Work carried out by Johnson Matthey Metal Joining suggests that most aqueous solutions will produce failures on susceptible joints to a greater or lesser degree. Joints exposed to the weather have also failed, but only after several years of exposure.

#### Materials Affected by Interfacial Corrosion

All types of stainless steel are susceptible to attack by interfacial corrosion. The nickel-free, or low nickel ferritic and martensitic type stainless steels (e.g. Types 403, 410, 416, 420, 430, 431) are most susceptible to interfacial corrosion and suffer a more rapid rate of attack than the austenitic steel grades (e.g. Types 302, 303, 304, 316, 321).

Failures with ferritic stainless steels have been reported within as little as a few days, while the austenitic steels under the same conditions have resisted attack for periods in excess of a few months. Austenitic grades of stainless steel are more resistant but failures are still common.

#### The Effects of Interfacial Corrosion

Interfacial corrosion results in failure of a joint with corrosion running across the joint interface. Often a failed joint does not appear to have been brazed properly in the first place. Although, if the joint had been tested after brazing, it would have had adequate strength. It is typical that the extreme outer edge of the brazing filler metal will remain attached to the parent materials giving a 'halo' effect. It is sometimes possible to see the first signs

of interfacial corrosion attack within as little as 30 minutes, as small rust spots begin to form towards the edge of the filler metal deposit. Over time the rust spots grow forming a continuous band of corrosion.



#### Filler Metals Resistant to Interfacial Corrosion

In addition to Argo-braze™ 632 and Argo-braze™ 56 there are also a number of other filler metals which offer protection against interfacial corrosion.

Filler Metal Type	Filler Metal Product	Resistant	Comments
Soft Solders	Silver-tin soft solder - P40™ Copper-tin soft solder - 99C™, 97C™	Yes	Lower strength and service temperature than a brazed joint.
Silver based	Silver-flo™ Products	No	Silver-flo™ filler metals are least resistant to interfacial corrosion
	Argo-braze™ Products - Argo-braze™ 502, Argo-braze™ 40	Yes/No	Argo-braze™ products containing nickel offer greater resistance particularly on austenitic steels.
Palladium based	Pallabraz™ Products	Yes	Cost and the brazing process (furnace brazing) are considerations
Gold based	Orobraz™ Products	Yes	Cost and the brazing process (furnace brazing) are considerations
Nickel based	Nickelbraz™ HTN Products	Yes	The brazing process (furnace brazing) is a consideration
Copper based	B Bronze™ and C Bronze™	Yes	The brazing process (furnace brazing) is a consideration

#### Other Methods of Prevention

Protection can also be provided by the application of a coating, which will prevent the service environment coming in contact with the brazing filler metal. Plating may be considered but care is necessary since joints may be

produced that are partially corroded as a result of attack from the plating solution. An application of soft solder over the brazing filler metal is one method, which has also been adopted.

#### Summary

Interfacial corrosion is a complex phenomenon, which is not completely understood. Consequently a positive guarantee that any particular joint will not fail cannot be made. Wherever it is likely to be a service hazard and the application is of a critical nature then tests should be conducted. If the

application is not critical, one of the recommended alloys, which appears to offer resistance under most conditions, should be used. It should be noted that brazed joints can have different service environments on the inside and outside of the joint.

Johnson Matthey  
 Platinum Group Metal Services  
 Orchard Road,  
 Royston, SG8 5HE  
 United Kingdom

Email: [mj@matthey.com](mailto:mj@matthey.com)  
[www.matthey.com](http://www.matthey.com)



Johnson Matthey Plc cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products will be used. This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is given in good faith, being based on the latest information available to Johnson Matthey Plc and is, to the best of Johnson Matthey Plc's knowledge and belief, accurate and reliable at the time of preparation. However, no representation, warranty or guarantee is made as to the accuracy or completeness of the information and Johnson Matthey Plc assumes no responsibility therefore and disclaims any liability for any loss, damage or injury howsoever arising (including in respect of any claim brought by any third party) incurred using this information. The product is supplied on the condition that the user accepts responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. Freedom from patent or any other proprietary rights of any third party must not be assumed. The text and images on this document are Copyright and property of Johnson Matthey. This datasheet may only be reproduced as information, for use with or for resale of Johnson Matthey products. The JM logo®, Johnson Matthey name® and product names referred to in this document are trademarks of Johnson Matthey Plc, Royston, United Kingdom.